

RECEIVED
CENTRAL FAX CENTER
SEP 12 2006

Application No. 10/811,249
Attorney Docket No: 25307A

IN THE CLAIMS

1. (Currently Amended) A method of forming a non-biodegradable preform for a muffler having a predetermined shape comprising the steps of:
 feeding sugar and glass fibers into a preform mold having a predetermined shape of a muffler,
said sugar being fed into said preform mold prior to said feeding of said glass fibers into said preform mold, wherein the sugar comprises approximately 2-10 %, by weight, of the preform;
 heating said preform mold to a temperature sufficient to melt said sugar, said melted sugar adhering to said glass fibers to form sugar-coated glass fibers; and
 cooling said preform mold to bind said sugar-coated glass fibers together and form said non-biodegradable preform.
2. (Original) The method of claim 1, wherein said glass fibers are continuous glass strands.
3. (Original) The method of claim 2, further comprising the step of:
 texturizing said continuous glass strands by separating said continuous glass strands into individual glass fibers prior to feeding said continuous glass strands into said preform mold.
4. (Canceled)
5. (Previously Presented) The method of claim 1, wherein said predetermined shape of said preform mold has a shape corresponding to a shape of an automobile muffler.
6. (Original) The method of claim 1, further comprising the step of:
 removing said preform from said preform mold.
7. (Original) The method of claim 1, wherein said sugar is a sugar having a melting point of 130 °F or greater.
8. (Original) The method of claim 1, wherein said preform mold is perforated.
9. (Original) The method of claim 8, wherein said heating step comprises passing heated air through said preform mold for a period of time sufficient to at least partially caramelize said sugar.

Application No. 10/811,249
Attorney Docket No: 25307A

10. (Original) The method of claim 8, wherein said cooling step comprises passing cool air through said preform mold.
11. (Currently Amended) A method of forming a preform comprising the steps of:
placing a binder on internal walls of a preform mold prior to adding continuous glass strands to said preform mold;
adding said continuous glass strands to said preform mold; and
curing said binder to bond glass fibers positioned adjacent to said internal walls of said preform mold together and form said preform, said bonded glass fibers forming an encapsulating shell of ~~bound~~ glass fibers bonded by said binder, said bonded glass fibers surrounding internal ~~unbound~~ glass fibers not bonded by said binder within said preform;
wherein said binder is present ~~in the shell~~ on an external surface of said preform and is not located throughout said preform, and
wherein said ~~unbound~~ fibers not bonded by said binder are internal with respect to the encapsulating shell and are not located adjacent to said internal walls.
12. (Original) The method claim 11, wherein said binder is a sugar having a melting point of 130 °F or greater.
13. (Currently Amended) The method of claim 12, wherein said curing step comprises the steps of:
heating said preform mold to a temperature sufficient to at least partially melt said sugar, said melted sugar adhering to said glass fibers adjacent to said internal walls to form sugar-coated glass fibers; and
cooling said preform mold to bind said sugar-coated glass fibers together and form said encapsulating shell of said preform.
14. (Original) The method of claim 13, further comprising the step of:
heating said preform mold prior to placing said sugar on said internal walls.
15. (Original) The method of claim 11, further comprising the step of:
texturizing said continuous glass strands by separating said continuous glass strands into individual glass fibers prior to feeding said continuous glass strands into said preform mold.

Application No. 10/811,249
Attorney Docket No: 25307A

16. (Original) The method of claim 11, further comprising the step of:
removing said preform from said preform mold.

17. – 20. (Canceled)